

TECHNICAL INFORMATION

2585 Aura


TECHNICAL SPECIFICATIONS ACCORDING TO EN 1307

constructie	<i>construction</i>	ISO 2424	5/64" soft saxony
poolmateriaal	<i>yarn content</i>	ISO 2424	polyamide PA 6
rug	<i>backing</i>	ISO 2424	Comfort Backing
gebruiksklasse	<i>suitability</i>	EN 1307	23/33 heavy contract use
poolgewicht	<i>pile weight</i>	ISO 2424	3200 gr/m ²
totaal gewicht	<i>total weight</i>	ISO 8543	4150 gr/m ²
poolhoogte	<i>pile height</i>	ISO 1766	14,5 mm
totaal hoogte	<i>total height</i>	ISO 1765	16 mm
noppental	<i>tuft density</i>	ISO 1763	372960 tufts/m ²
breedte	<i>width</i>	CEN/TS 14159	ca 4 m
warmtedoorlaatweerstand	<i>thermal resistance</i>	ISO 8302	0.15 m ² K/W
brandklasse	<i>flammability</i>	ISO 13501-1	Cfl-s1
contactgeluidsisolatie	<i>impact sound insulation</i>	ISO 140-8/717-2	25 dB
structure	<i>Konstruktion</i>	ISO 2424	5/64" soft saxony
composition	<i>Polmaterial</i>	ISO 2424	polyamide PA 6
dossier	<i>Beschichtung</i>	ISO 2424	Comfort Backing
classement d'usage	<i>Zusatzeignung</i>	EN 1307	23/33 heavy contract use
poids de velours	<i>Poleinsatzgewicht</i>	ISO 2424	3200 gr/m ²
poids total	<i>Gesamtgewicht</i>	ISO 8543	4150 gr/m ²
hauteur du velours	<i>Polschichthöhe</i>	ISO 1766	14,5 mm
hauteur totale	<i>Gesamthöhe</i>	ISO 1765	16 mm
densité	<i>Noppenzahl</i>	ISO 1763	372960 tufts/m ²
dimensions	<i>Breite</i>	CEN/TS 14159	ca 4 m
résistance thermique	<i>Wärmedurchlasswiderstand</i>	ISO 8302	0.15 m ² K/W
comportement au feu	<i>Brandverhalten</i>	ISO 13501-1	Cfl-s1
isolation acoustique	<i>Trittschallverbesserungsmaß</i>	ISO 140-8/717-2	25 dB

COLOURS

102 Rice	149 Putty	199 Ebony
112 Quinoa	153 Honey	
129 Silver	183 Camouflage	
139 Gray	189 Soil	

PRODIS RATING AND INFORMATION



EN 14041
EN 1307

PRODIS: 1025-130943

CONTACT INFORMATION

THE NETHERLANDS
(HEAD OFFICE)
NIJVERHEIDSTRAAT 39
NL - 8281 JD GENEMUIDEN
+31 (0)38 385 22 11
INFO@EDEL CARPETS.COM
WWW.EDEL CARPETS.COM

geproduceerd door / *manufactured by*
fabriqué par / *hergestellt durch*

edel carpets®
since 1918

All technical specifications are subject to normal manufacturing tolerances. For all Terms & Conditions, care and maintenance, please visit our website.

All specifications are subject to normal manufacturing tolerances. For all Terms & Conditions, care and maintenance, please visit our website.

Toutes les spécifications techniques sont sujet aux tolérances de fabrication. Merci de consulter notre website pour toutes informations et les conseils d'entretien.

All technical data are subject to normal production tolerances. Conditions and care recommendations can be found on our website.

v2